

Applicability of SS70-A310

In response to your request to clarify whether this printing use solder paste can be applied for a dispensing application, a dispense test was conducted under the below test conditions.

- Needle diameter: 0.25mm
- Dispense temp. 30C
- Dispense pressure: 0.10Mpa
- Dispense time: 0.1sec
- Stand-off: 0.2mm

Observing the results, it was concluded that this solder paste can be dispensed at least subject to the above conditions are concerned.

We, therefore, agreed to fill this product in a syringe according to your request, but the following conditions must be agreed in advance.

As long as the product is supplied in a syringe, its warranted product shelf life is “3 months” from the manufacturing date.

Koki Company Limited

村田 修一